

Purolite® A850

**Polyacrylic Gel Strong Base Anion
Resin Chloride form**

PRINCIPAL APPLICATIONS

- Organic Matter Removal
- Tannin removal
- Demineralization
- Acid Retardation

TYPICAL PACKAGING

- 1 CF Sack
- 25 L Sack
- 5 CF Drum (Fiber)
- 1 M³ Supersack
- 42 CF Supersack

ADVANTAGES

- Excellent resistance to organic fouling

REGULATORY APPROVALS

- IFANCA Halal Certified
- Kosher Certified
- Certified by the WQA to NSF/ANSI-61 Standard

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polyacrylic crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Quaternary Ammonium
Ionic Form	Cl
Total Capacity	1.25 eq/L (27.3 Kgr/ft³) (Cl form)
Moisture Retention	57 - 62 %
Particle Size Range	300 - 1200 µm
< 300 µm (max.)	1 %
Uniformity Coefficient (max.)	1.7
Irreversible Swelling (max.)	10 %
Reversible Swelling, Cl OH (max.)	15 %
Specific Gravity	1.09
Shipping Weight (approx.)	680 - 730 g/L (42.5 - 45.6 lb/ft³)
Temperature Limit	35 °C (95.0 °F) (OH form)

Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

Europe
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com

