

Purolite® A860

Polyacrylic Macroporous Chloride form

Sugar Grade

PRINCIPAL APPLICATIONS

- Decolorization - Sugar Solutions
- Organic Scavenger
- Organics removal

TYPICAL PACKAGING

- 1 CF Sack
- 25 L Sack
- 5 CF Drum (Fiber)
- 1 M³ Supersack
- 42 CF Supersack

ADVANTAGES

- Excellent removal of organic matter
- Efficient regeneration
- Good resistance to organic fouling

REGULATORY APPROVALS

- IFANCA Halal Certified
- Kosher Certified
- Certified by the WQA to NSF/ANSI-61 Standard

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Macroporous polyacrylic crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Quaternary Ammonium
Ionic Form	Cl
Total Capacity	0.8 eq/L (17.5 Kgr/ft³) (Cl form)
Moisture Retention	66 - 72 % (Cl form)
Particle Size Range	300 - 1200 µm
Uniformity Coefficient (max.)	1.7
Reversible Swelling, Cl OH (max.)	20 %
Specific Gravity	1.08
Shipping Weight (approx.)	680 - 730 g/L (42.5 - 45.6 lb/ft³)
Temperature Limit	80 °C (176.0 °F) (Cl form)



Americas
 T +1 610 668 9090
 F +1 610 668 8139
 americas@purolite.com

Europe
 T +44 1443 229334
 F +44 1443 227073
 europe@purolite.com

Asia Pacific
 T +86 571 876 31382
 F +86 571 876 31385
 asiapacific@purolite.com