

# Purolite® TANEX™

**Macroporous Type I Strong Base  
Anion Resin Chloride form**

## PRINCIPAL APPLICATIONS

- Organic Matter Removal
- Tannin removal

## TYPICAL PACKAGING

- 1 CF Sack
- 25 L Sack
- 5 CF Drum (Fiber)
- 1 M<sup>3</sup> Supersack
- 42 CF Supersack

## TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Styrene and Acrylic crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Quaternary Ammonium
Ionic Form	Cl
Moisture Retention	68 - 75 % (Cl form)
Particle Size Range	300 - 1200 µm
< 300 µm (max.)	1 %
Uniformity Coefficient (max.)	1.7
Shipping Weight (approx.)	600 - 700 g/L (37.5 - 43.8 lb/ft <sup>3</sup> )
Temperature Limit	60 °C (140.0 °F) (Cl form)

**Americas**  
T +1 610 668 9090  
F +1 610 668 8139  
americas@purolite.com

**Europe**  
T +44 1443 229334  
F +44 1443 227073  
europe@purolite.com

**Asia Pacific**  
T +86 571 876  
31382  
F +86 571 876  
31385  
asiapacific@purolite.  
com

