

TULSION[®] **MB-115 BG**

Mixed Bed Ion Exchange Resin for Production of Ultra Pure Water

TULSION[®] MB-115 BG is a mixture of strongly acidic black cation exchange resin **TULSION[®] T-42** in Hydrogen form and strongly basic type I anion exchanger resin **TULSION[®] A-23** in Hydroxide form in 1:1.5 volume ratio quantities.

TULSION[®] MB-115 BG is designed for use in the final polishing for production of ultra pure water.

TULSION[®] MB-115 BG is the ideal choice for electronic industries, which manufacture semi conductors and television tubes, etc where ultra pure water is required. This resin combines high capacity with excellent physical properties.



TYPICAL CHARACTERISTICS – MB- 115(BG)

	TULSION T-42	TULSION A-23
Type	: Strong acid cation exchange resin	Strong base anion exchange resin
Matrix structure	:	Polystyrene copolymer
Functional group	: Sulphonic acid	Quaternary ammonium Type II
Physical form	:	Moist Spherical Beads
Ionic form	: Hydrogen	Hydroxide
Screen Size USS (wet)	:	16 to 50
Particle size	:	0.3 to 1.2 mm
Fines content	:	Less than 0.5% passing through 50 US mesh
Total exchange capacity	: 1.8 meq/ml min of 99% in Hydrogen form	1.0 meq/ml min of 95% in hydroxide form
Temperature stability (max)	:	40° C
Backwash settled density	:	710 to 750 g/l
Organic leachable	:	Less than 0.2 mg KMnO ₄ / ml of wet resin
Impurities	:	Fe not more than 200 ppm Cu not more than 100 ppm
Bead strength	: Average not less than 500 g/bead by Chatillion test	Avg. not less than 300 g/bead by Chatillion test
pH range	:	0 to 14
Solubility	:	Insoluble in all common solvents

TESTING

The sampling and testing of ion exchange resins is done as per standard testing procedures, namely ASTM-D-2187 and IS-7330, 1998.

PACKING

Super sacks	1000 liters
MS drums	180 liters
HDPE lined bags	25 liters

Super sacks	35 cft
Fiber drums	7 cft
HDPE lined bags	1 cft

For Handling, Safety and Storage requirements please refer to the individual Material Safety Data Sheets available at our offices. The data included herein are based on test information obtained by Thermax Limited. These data are believed to be reliable, but do not imply any warranty or performance guarantee. Tolerances for characteristics are as per BIS/ASTM. We recommend that the user should determine the performance of the product by testing on own processing equipment.

For further information, please contact:



THERMAX

THERMAX LIMITED
CHEMICAL DIVISION

An ISO 9001 Company
97-E, GENERAL BLOCK,
M.I.D.C. BHOSARI,
PUNE 411 026, INDIA
TEL : +91(20) 2712 0181, 2712 0169
FAX : +91(20) 2712 0206
E-mail : resins@thermaxindia.com
Website : www.thermaxindia.com/chemical

USA Office :
THERMAX INC.
40440 Grand River Avenue,
Novi, Michigan 48375
U.S.A.
Tel : 248-474-3050
Fax : 248-474-5790

In view of our constant endeavour to improve the quality of our products, we reserve the right to change their specifications without prior notice.

TCD/PMG/June '06