

## SALES SPECIFICATION SHEET

## FILTRASORB 600 AR+ 12X40

Granular Activated Carbon

|                                                    | Specification |      |                                    |
|----------------------------------------------------|---------------|------|------------------------------------|
| Test                                               | Min           | Max  | Calgon Carbon<br>Test Method       |
| IODINE NUMBER 1999/9                               | 005           |      | TM 4 ACTM D4C07                    |
| IODINE NUMBER, mg/g<br>MOISTURE (AS PACKAGED), wt% | 825           | 2    | TM-4,ASTM D4607<br>TM-1.ASTM D2867 |
| ABRASION NUMBER                                    | -<br>75       | _    | TM-9,AWWA B604                     |
| WATER SOLUBLE ASH, wt%                             | -             | 1    | TM-16                              |
| EFFECTIVE SIZE, mm                                 | 0.55          | 0.75 | TM-47,ASTM D2862                   |
| ASH, wt%                                           | -             | 10   | ASTM D2866,TM-5                    |
| 12 US MESH [1.70 mm], wt%                          | _             | 5    | TM-8,ASTM D2862                    |
| < 40 US MESH [0.425 mm] (PAN), wt%                 | -             | 5    | TM-8,ASTM D2862                    |

## **Typical Properties:**

This product complies with the requirements for activated carbon as defined by the Food Chemicals Codex (FCC) (Latest Edition) published by the U.S. Pharmacopeia.

Only products bearing the NSF Mark are Certified to NSF/ANSI 61 - Drinking Water System Components - Health Effects standard. Certified Products will bear the NSF Mark on packing or documentation shipped with the product.

Calgon Carbon Corporation's activated carbon products are continuously being improved and changes may have taken place since this publication went to press. (12124-03/28/2016)